

Sub P1

13. A method as set forth in claim 1 where a combination of sizing methods to produce improved sizing measurements is used according to Figure 9.

5

ABSTRACT OF THE INVENTION

Sub P1

10 A method for sizing crack is disclosed using a combination of depth crack sizing methods to improve crack sizing accuracy for thin walled tubing and tight crack surface opening less than 0.001 inches for cracks of any depth. The tube or plate wall can consist of a single material or multiple metallic electrodeposited or otherwise intimately bonded layers of materials with different magnetic properties and the sizing method comprises known depth sizing methods such as shear wave, time of flight and THE SELECTIVE USE OF two unique depth sizing methods designated as Mode Converted Signal (MCS) and Full Skip Normalization (FSN) which provide correction factors for the known sizing methods.

15

20